



Silage
FORMULA

TECHNICAL DATA SHEET

Property	Test method	Unit	General Data and Value
Thickness	DIN 53370	um	200
UV stabilization	DIN EN ISO 4892-2	MJ.m ⁻²	8400
Chemical resistance			High resistance against acids
Property	Test method	Unit	Typical Values
Stress at break MD TD	DIN EN ISO 527	MPa	21
			21
Strain at break MD TD	DIN EN ISO 527	%	620
		%	770
Force at break MD TD	DIN EN ISO 527	N/cm	42
		N/cm	42
Dart-Drop plain	ASTM D1709-62	G	630
Oxygen permeability	DIN 53380-3	cm ³ /m ² in 24 h	120

No warranty or guarantee expressed or implied is made regarding the performance of the product, since the manner of use and handling is beyond our control

ABN 16 004 575 964

10-12 George St Sandringham VIC 3191
Tel: 03 9597 0777 Email: sales@geoffmiller.com.au
www.geoffmiller.com.au